

Formulation guideline

Market: Cosmetics
 Product: Pressed Powder
 Code: GL-243403
 Special effect pigment: Geoparl C Crystal Silk Terracotta Brown |
 Geoparl C Crystal Bronze



Product name	INCI name	% WT.	Supplier
A			
Sunrise SVA	Mica (and) Lauroyl Lysine	10,0	Geotech International B.V.
Sunrise 970	Mica	7,0	Geotech International B.V.
Zinc Stereate	Zinc Stereate	7,0	
Boroneige 1501	Boron Nitride	2,5	ESK
Luzenac 00	Talc	23,5	Luzenac
B			
Fragrance		q.s.	
Antioxidant		q.s.	
Preservative		q.s.	
C			
DC 200 Fluid 5cts	Dimethicone	6,25	Dow Corning
DC 9040 Elastomer	Cyclomethicone (and) Dimethicone Crosspolymer	6,25	Dow Corning
D			
Geoparl C Crystal Silk Terracotta Brown	Synthetic Fluorophlogopite (and) CI 77491 (and) CI 77492 (and) CI 77499 (and) Triethoxycaprylylsilane	27,5	Geotech International B.V.
Geoparl C Crystal Bronze	Synthetic Fluorophlogopite (and) CI 77491	12,5	Geotech International B.V.

Procedure

1. Thoroughly blend Phase A in a blender
2. Add phase B to phase A and mix until uniform;
3. Add phase C to phase AB and mix until uniform;
4. Add phase D to phase ABC and mix until uniform;
5. Press the powder.

For formulating support and colour matching requests please contact us on marketing@geotech.nl

This information and all technical advices are given in good faith and without warranty. This also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information provided and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and therefore entirely your own responsibility.

Geotech International B.V. | Emrikweg 18 | 2031 BT | Haarlem | The Netherlands
 T: +31(0)235317553 | E: info@geotech.nl | www.geotech.nl